## (19) 世界知的所有権機関 国際事務局



## 

## (43) 国際公開日 2005 年1 月27 日 (27.01.2005)

**PCT** 

## (10) 国際公開番号 WO 2005/007577 A1

(51) 国際特許分類7: C01G 53/00, H01M 4/02, 4/58, 10/40

(21) 国際出願番号:

PCT/JP2004/010238

(22) 国際出願日:

2004年7月12日(12.07.2004)

(25) 国際出願の言語:

日本語

(26) 国際公開の言語:

日本語

(30) 優先権データ:

特願2003-199205 特願2003-208657 2003 年7 月18 日 (18.07.2003) JF 2003 年8 月25 日 (25.08.2003) JF


(71) 出願人 (米国を除く全ての指定国について): 東ソ一株 式会社 (TOSOH CORPORATION) [JP/JP]; 〒746-8501 山口県 周南市 開成町 4 5 6 0 番地 Yamaguchi (JP). (72) 発明者; および

- (75) 発明者/出願人 (米国についてのみ): 藤井 康浩 (FUJII,Yasuhiro) [JP/JP]; 〒745-0851 山口県 周南市 大字徳山5536番地 Yamaguchi (JP). 鈴木 直人 (SUZUKI,Naoto) [JP/JP]; 〒746-0024 山口県 周南市 古泉 2-17-2 Yamaguchi (JP). 庄司 孝之 (SHOJI,Takayuki) [JP/JP]; 〒746-0011 山口県 周南市 土井2丁目15-4-102 Yamaguchi (JP). 国吉実 (KUNIYOSHI,Minoru) [JP/JP]; 〒753-0212 山口県山口市下小鯖字山ノ神887-37 Yamaguchi (JP). 岩田英一 (IWATA,Eiichi) [JP/JP]; 〒746-0011 山口県周南市土井2丁目15-4-205 Yamaguchi (JP).
- (74) 代理人: 小栗 昌平, 外(OGURI Shohei et al.); 〒107-6013 東京都港区 赤坂一丁目 1 2番 3 2号 アーク森 ビル 1 3階 栄光特許事務所 Tokyo (JP).

[続葉有]

(54) Title: LITHIUM-NICKEL-MANGANESE COMPOSITE OXIDE, PROCESS FOR PRODUCING THE SAME AND USE THEREOF

(54) 発明の名称: リチウム-ニッケル-マンガン複合酸化物及びその製造方法並びにその用途



D...INTENSITY

(57) Abstract: A positive electrode material for lithium ion secondary battery, exhibiting high discharge capacity and excelling in rate characteristics and cycle characteristics. The battery is characterized in that a lithium-nickel-manganese composite oxide wherein the composition is represented by the formula  $\text{Li}_x \text{Ni}_y \text{Mn}_z \text{O}_2$  (wherein x is  $1+1/9\pm(1+1/9)$ , y is  $4/9\pm(4/9)/10$  and z is  $4/9\pm(4/9)/10$ ), the crystal structure belongs to a monoclinic system and the space group is C12/m1 (No. 12) is used as a positive electrode material. With respect to the lithium-nickel-manganese composite oxide, it is preferred that on face (002) and face (13-3) in Miller index hkl at monoclinic system C12/m1 (No. 12) attribution, the powder X-ray diffraction peak intensity ratio  $I_{(002)}/I_{(13-3)}$  measured with the use of Cu-K  $\alpha$  rays be 1.35 or higher.

D 磁網